BATHROOM+

PRODUCT USES

Suitable for interiors that suffer from high condensation. Not suitable for areas that are continually soaked with water, e.g. shower enclosures.

Attractive soft sheen finish for bathrooms

FEATURES AND BENEFITS

Moisture and steam resistant – Ideal for high condensation areas.

Mould resistant – MouldTec Technology

Exceptionally durable and washable.

Preserved air quality - Low VOC, less than 16 g/L.

PRODUCT INFORMATION

Appearance	Soft Sheen
Colour	Pure Brilliant White
Density at 23°C	Approx. : 1.23 kg/L
Solids Content	By weight : Approx. 50% By volume : Approx. 43%
Packaged Viscosity	Viscosity at 23°C : Approx 140 KU
Volatile Organic Compound	White < 16g/L
Spreading Rate	8 to 10m² per litre depending on surface porosity, profile and application method
Recommended DFT per coat	Min. 30µm. Max. 45µm.

APPLICATION INFORMATION

Application conditions	Surface Temperature between 10 - 35°C Relative Humidity between 10 - 85 %
Application methods	Brush, Roller or airless spray
Thinner	Thinning not recommended Ready for use after thorough stirring
Drying Time	Touch dry 45 minutes (Drying times will be extended during cold, wet or humid conditions)
Recoating Time	4 hours
Cleaning of equipment	Clean immediately with water
Substrates	Suitable for cement plaster, gypsum plaster, concrete, fibre cement, ceiling boards, provided that appropriate preparation and priming is carried out.

DULUX

TRIMS

BATHROOM+

2.5L

1L

PACK SIZES

APPLICATION INFORMATION

PRECAUTIONS

Ensure that surfaces are sound and free from dust, dirt, grease and oil. Surfaces must be thoroughly dry - no more than 12% moisture content.

Do not apply directly to bare metal surfaces.

Not suitable for painting radiators or other heated surfaces.

Do not paint when temperatures are below 10°C

Drying times will be extended during wet or cold weather conditions.

Do not apply directly to chalky or friable surfaces

Protect the paint from extreme weather conditions, particularly frost.

Allow at least 24 hours for the paint to fully dry before exposing to condensation.

Paint is not suitable for areas continually soaked with water such as shower enclosures

Coats Required

Apply two to three finishing coats to new surfaces to achieve a closed film and solid colour.

SURFACE PREPARATION

NEW SURFACES

Cement Plaster (non friable), Gypsum Plaster, Composition Boarding, Fibre Cement

It is recommended that fresh plaster should be allowed one week drying for every 5mm thickness; and longer in cold or damp weather.

Spot-prime metal strips and nail heads with appropriate metal primer.

Prime with **Dulux Plaster Primer**.

Rough surfaces may be filled with **Dulux Trade Fillercoat** to create a smooth base of even porosity.

Concrete

Remove any uncured cement, grease, and mould-release agents by high-pressure water blast, or wash with a strong solution of sugar soap. Rinse off thoroughly with clean water.

Prime with **Dulux Plaster Primer**.

PREVIOUSLY PAINTED SURFACES

Ensure that surfaces are sound and free from dust, dirt, grease and oil. Surfaces must be thoroughly dry - no more than 12% moisture content.

Sand enamel surfaces to provide a key and improve adhesion.

Sound, not powdery

Clean surfaces with Fixit Sugar Soap. Wash down with water.

For emulsion surfaces apply finishing coats.

For enamel surfaces, sand to a matt finish to aid adhesion and follow with a coat of **Dulux Undercoat for All Surfaces**. Apply finishing coats.

Old Paint in poor condition

Loose, flaking paint must be completely removed and bare areas spot primed with appropriate primer. It is always good painting practice to rub down existing surfaces with fine sandpaper to remove nibs and dirt particles. Rubbing down also provides a smooth surface for painting.

Mould instructions. To kill lichen and algae growth, scrub with 1 of the following solutions: either 4:1 water/HTH (chlorine), or 4:1 water/JIK (sodium hypochlorite). Ensure that the areas are completely saturated, and allow the solution to react for a minimum of 4 hours. Rinse the complete wall surface thoroughly with clean water.

Filling

Fill and repair imperfections with the appropriate **Fixit** filler and prime with **Dulux Plaster Primer** once the crack filler has dried properly. Failure to do this will result in uneven sheen levels between the repaired and normal areas.

HEALTH AND SAFETY INFORMATION

For detailed safety information refer to Material Safety Data Sheet.

Keep out of reach of children.

Ensure good ventilation during application and drying.

Non-flammable.

ADDITIONAL INFORMATION

Storage Conditions

Store under cool dry conditions.

Disclaimers

For best colour and sheen consistency, it is advisable to use containers of the same batch number, or to mix different batches together in a large container, or to finish in a corner before starting a new container.

ICI Dulux (Pty) Ltd PO Box 123704 Alrode 1451 8 Juyn Street Alrode Alberton 1450 Helpline 0860 330 111 Tel +2711 861 1000
Fax +2711 864 6701 Email info@dulux.co.za. www.dulux.co.za www.akzonobel.com