

Stratigraphy

- 1 PE film
- 2 Waterproofing mass
- 3 Single strand composite polyester reinforcement
- 4 Waterproofing mass
- 5 Sand or talc finish

Characteristics

JAYCO TORCH HP is a prefabricated membrane made of bitumen distillate modified with elasto-plastomeric polymers reinforced with spunbond non-woven polyester filaments stabilized with fibreglass.

The waterproofing compound obtained through the complete homogenization of bitumen distillate with elasto-plastomeric polymers added with special additives provides excellent features:

- resistance to U.V. radiation
- resistance to temperature change
- resistance to O₃
- resistance to chemical corrosion (acids and salts)
- waterproof seal

Finishing

The upperside of JAYCO TORCH HP is finished with a special inorganic material with extremely fine release material which is uniformly spread and calibrated in order to prevent the roll from sticking to itself. The underside is protected by a burn-off printed polyethylene film that allows you to check anytime the ideal melting point of the waterproofing compound.

Methods of application

- The membrane is usually applied by heating the bituminous blend using a gas burner or hot air guns in special cases.
- Always use the individual protection devices specified by law.
- Never use application by heating on heat-sensitive supports or insulation.
- Conduct regular maintenance on the roof in order to remove detritus, mud, grass, etc., and to keep the operation of the waterproofing system and accessories (drains, TV antennas, air-conditioning systems, etc.) under control.
- Whenever there is reason to believe that the element to be waterproofed has traces of residual humidity (e.g. during renovations of existing roof coverings, applications after abundant rainfall), vents should be positioned in such way as to permit its elimination.

For more information and instructions, we recommend consulting LARIBIT application manual, remembering that our Technical Support Service is always at your disposal to solve particular problems and provide the assistance necessary in using our waterproofing membranes to best advantage.

Fields of use



EN13707 Continuous roofs (Certificate n° GB14/92056)





N° LAYERS			METHOD OF APPLICATION					TYPE OF APPLICATION			TYPE					
Single Layer	• Double Layer	• Multilayer	• Torch	Hot Air	Mixed (Torch / Air)	Cold Bond Glue	Mechanical Fixing	Thermo Adhesive / Self Adhesive	• Fully Bonded	Partially Bonded	Loose Laid	• Complimentary Layer	Top Layer	Heavy Protection	Anti-root	Other Uses

JAYCO TORCH HP P 3 MM

The waterproofing membrane based on distilled bitumen and polymers, as shown in this data sheet does not require the issue of a MSDS, because it does not contain dangerous substances. The information data sheet for the proper use of products is available.

Application

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300/400 g/m².
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point. (Draw. N.1)
- Position the membrane sheets staggered, avoiding to create any overlaps against the slope and the drains. (Draw. N.2)
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10 x 10 cm). (Draw. N.3)
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm. (Draw. N.3)
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet. (Draw. N.4)
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.



Jayco Torch HP

Recommendations

- Rolls of product must be stored upright in suitable areas (roofed and ventilated) far from sources of heat, and must never be stacked one on top of another in order to prevent deformation that may compromise laying. Store the product at temperatures higher than 0°C.
- The application surface must be smooth, dry, and clean.
- The application surface must be previously treated with the appropriate bituminous primer.
- The application surface must always be even and smooth and with sufficient slope (min. 1.5 %) to prevent ponding water.
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The product must be applied at room temperatures of above + 5°C.
- Application must be suspended during inclement weather (excessive humidity, rain, etc.).
- The materials without mineral self-protection or P+V, used as a top layer (cap sheet), can be painted with an aluminium coating to improve and extend the performance and life expectancy, the material should be allowed to oxidize approx. 3-6 months before being coated. An alternative, depending on the type of construction, it is possible to use heavy protection (floating pavements, stone, etc.).
- The pallets supplied are suited only for normal warehouse movement and not for raising heavy loads to height.
- We recommend making correct and regular warehouse rotation.

Technical data

Technical Characteristics	Measure Units	Reference Norm	P	Tolerance
Type of reinforcement			Single strand polyester	
Upper face finish			Sand or talc	
Lower face finish			PE film	
Watertightness	kPa	EN 1928	60	
Length	m	EN 1848-1	15 -1%	
Width	m	EN 1848-1	1 -1%	
Thickness	mm	EN 1849-1	3	±5%
Cold flexibility	°C	EN 1109	-10	
Flow resistance	°C	EN 1110	120	
Flow resistance after ageing	°C	EN 1296	110	-10°C
Tensile strength L / T	N / 5 cm	EN 12311-1	600/500	-20%
Elongation at break L / T	%	EN 12311-1	40/40	-15
Tearing resistance L / T	N	EN 12310-1	150/150	-30%
Static puncture resistance	kg	EN 12730	15	
Dynamic puncture resistance	mm	EN 12691	900	
Dimensional stability	%	EN 1107-1	-0,5	
Fire resistance		EN 13501-5	F ROOF	
Fire reaction		EN 13501-1	F	

Sizes & packing

	P 3 mm
Rolls size [m]	10x1
Rolls per pallet	30
Square meters per pallet [m ²]	300

Sizes & packing may vary depending on the type of transportation. The technical data given is based on average values obtained during production. Laribit reserves the rights to change or modify the nominal values without prior notice or advice. The information contained in this data sheet are based on our experience. We cannot take any responsibility for a possible incorrect use of the products. The customer has to choose under their own responsibility a product fit for the intended use.

Laribit®

Laribit S.r.l. - Via Orazio Andreoli 7
37059 Santa Maria di Zevio (VR) Italy

Tel. +39 045 8775559 www.laribit.com
Fax +39 045 8751474 info@laribit.com

