

PROFESSIONAL HYGIENE LOW SHEEN

PRODUCT CODE: PHL 1 & THL 1000

TECHNICAL DATA SHEET

Product Description	Low sheen acrylic emulsion.													
Intended Uses	<ul style="list-style-type: none"> For interior use. Suitable for correctly primed new plaster, concrete, porous brickwork and various types of building boards. 													
Features & Benefits	<ul style="list-style-type: none"> BIODEFENCE™ silver technology actively inhibits microbial growth between cleanings BIODEFENCE™ promotes a more hygienic environment BIODEFENCE™ helps reduce the risk of cross-contamination via painted surfaces Low VOC Excellent washability and stain resistance Ease of application and good hiding 													
Product Information	Appearance	Low sheen												
	Colour	White (PHL 1)												
	Tint Bases	Pastel Tint Base (THL 1000)												
	Volume solids	40 %												
	Recommended DFT	25 – 35 µm												
	Recommended WFT	63 – 88 µm												
	Theoretical spreading rate	13.3 m ² /L @ 30 µm DFT per coat. This serves as a guide only												
	Practical spreading rate	The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.												
	TVOC	<16 g/L for White and Pastel bases												
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous.												
	Method	Brush, roller or airless spray.												
	Thinning	Ready for use, no thinning required												
	Cleaning	Water												
	Drying time	Touch dry: 30 mins @ 23 °C Over coating: 1 h @ 23 °C												
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10 %</td> </tr> <tr> <td colspan="3">Or 3 °C min above dewpoint</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85 %</td> </tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10 %	Or 3 °C min above dewpoint			Max: 40 °C	Max: 40 °C	Max: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10 %												
Or 3 °C min above dewpoint														
Max: 40 °C	Max: 40 °C	Max: 85 %												
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 20 L													
Tint Bases	<ul style="list-style-type: none"> The tint base containers are underfilled to levels which are specific for each tint base to allow for a calculated volume of colourants to be added. The volume indicated on the container is only achieved after the addition of all prescribed colourants as per the formulation. The tint bases and the colourants are unfinished or intermediate products which are not recommended for use by themselves. A finished product is only produced once the prescribed quantities of colourants have been thoroughly mixed with the tint base. When mixed to a finished product its technical features, product information, application and surface preparation details comply with that of PROFESSIONAL HYGIENE LOW SHEEN (PHL 1). <p>N.B. Only colourants from the Plascon Inspired colour system are permitted for use when tinting.</p>													

PROFESSIONAL HYGIENE LOW SHEEN

PRODUCT CODE: PHL 1 & THL 1000

TECHNICAL DATA SHEET

Tinting Procedure	<ul style="list-style-type: none"> Select the required colour and reference no. from the INSPIRED COLOUR fandeck, other suitable fandecks or colour cards and locate the applicable formulation from the tables. Certain colour choices may require more than two coats to achieve full obliteration (see computer formulations for details in remarks column prior to tinting) Select the required volume for tinting and set the tinting machine to deliver the correct amount of colourants as per formulation. Inject all required colourants, close container and shake on mechanical shaker for 5 minutes. Note: UNDER NO CIRCUMSTANCES SHOULD COLOURS BE TINTED FROM PROFESSIONAL HYGIENE LOW SHEEN WHITE (PHL 1) - USE ONLY THE PRESCRIBED TINT BASE (THL 1000).
Surface Preparation	<p>Ensure that surfaces are dry, sound, and free from dust, dirt, grease and oil before painting.</p> <ol style="list-style-type: none"> NEW WORK <ol style="list-style-type: none"> <u>Cement plaster, concrete and porous brickwork:</u> Ensure concrete has dried for 4 weeks and cement plaster for 2 weeks. Apply one coat of PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700). <u>Gypsum plaster (e.g. Rhinolite, Cretestone), brickwork stone work:</u> Apply one coat of PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700). If a gypsum plaster has been used as the joint skimming filler on gypsum board or dry wall partitioning, then seal these areas with PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700). <u>Fibre cement board:</u> Prime with BONDING LIQUID (CV1 14) or PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700) <u>Wood:</u> Sand to a smooth finish and dust off. Seal knots and resinous areas with KNOT SEAL (PK 2). Fill defects with POLYCELL MENDALL 90. Sand after 16 hours and spot prime. Prime with PROFESSIONAL WOOD PRIMER (PP 800) <u>Mild Steel:</u> Degrease with AQUASOLV DEGREASER (GR 1). Rinse thoroughly with water. Remove any rust by coarse sanding, mechanical grinding etc. or REMOVAL RUST REMOVER & CONCRETE ETCHER (RCC 170). Prime general surfaces the same day with ZINC PHOSPHATE PRIMER (UC 170) or PLASCOSAFE (EMS 18) <u>Galvanised iron:</u> Clean with GALVANISED IRON CLEANER (GIC 1) to achieve a water break-free surface. Rinse thoroughly with water. Prime the same day with PROFESSIONAL GALVANISED IRON PRIMER (PP 1000) PREVIOUSLY PAINTED SURFACES <ol style="list-style-type: none"> <u>Previously painted surfaces in good condition:</u> Remove loose and flaking paint back to a sound substrate and a firm edge by scraping and sanding. Clean with POLYCELL SUGAR SOAP POWDER CLEANER solution to remove all contaminants and chalked material. Rinse with clean water to remove all traces of sugar soap. Alternatively, rinse with high pressure water jet. Spot prime bare areas with the appropriate primer. Sand glossy enamel surfaces to a matt finish and apply one coat of PROFESSIONAL ALL PURPOSE UNDERCOAT (PU 800). <u>Previously painted surfaces in poor condition:</u> Completely remove paint by most appropriate means e.g. scraping, coarse sanding or stripping. Clean with POLYCELL SUGAR SOAP solution. Ensure substrate is sound, not powdery or friable, prior to coating. Treat as for new work. FILLING Fill all imperfections with POLYCELL MENDALL 90 or the appropriate POLYFILLA and spot prime filled areas with PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700).
Application	<ul style="list-style-type: none"> Apply two or more coats to suitably primed surfaces to achieve complete obliteration. Always maintain a wet edge and avoid downing tools during the application process to prevent lap marks and variances in colour or texture. Work from corner to corner or from a natural cut off point to another. Do not attempt touch ups but redo complete panels.
Caution	<ul style="list-style-type: none"> Do not thin. Thinning affects the properties of the product Although PROFESSIONAL HYGIENE LOW SHEEN is anti-bacterial, normal cleaning and washing procedures must be adhered to. Avoid painting during inclement weather or if temperature is below 10 °C

PROFESSIONAL HYGIENE LOW SHEEN

PRODUCT CODE: PHL 1 & THL 1000

TECHNICAL DATA SHEET

Safety Precautions

- Keep out of reach of children.
 - Ensure good ventilation during application and drying.
 - In case of skin contact, wash with soap and water or a recognised skin cleaner.
 - Avoid contact with eyes. In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
 - Harmful if swallowed. Do not induce vomiting. Seek medical attention.
 - Refer to Safety Data Sheet for complete information.
-

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B. Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

N.B. TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za