

Sikaflex®-Crystal Clear

Completely transparent multipurpose adhesive and sealant

Product Description

Sikaflex® Crystal Clear is a 1-component, solvent-free, multipurpose adhesive and sealant with a crystal clear appearance.

Uses

Sikaflex® Crystal Clear is designed as a multipurpose adhesive and is suitable for most surfaces including metal, glass, concrete, plaster, plasterboard, wood surfaces, painted enamel, polyester and plastics.

Sikaflex® Crystal Clear is designed as a sealant for vertical and horizontal indoor connection joints between partition walls, for metal and wood construction.

Characteristics / Advantages

- 100% crystal clear / transparent
- Good workability
- Low shrinkage during cure
- Especially for home improvement sector
- Can be used on damp concrete
- Very good adhesion on many typical building materials

Environmental Information

Specific Characteristics

- Solvent free
- Odourless
- Recyclable aluminium packaging (300 ml cartridges)

Specific Approvals/Standards

- EN 15651-1 F EXT-INT CC
- ISO 11600 F 20 LM



Product Data

Appearance / Colours	Transparent
Packaging	300 g cartridge (290 ml), 12 cartridges per box
Storage Conditions / Shelf-Life	12 months from date of production if stored in undamaged original unopened containers, in dry conditions and protected from direct sunlight at temperatures between +5°C and +25°C.

Technical Data

Chemical Base	Silane terminated polymer
Density	~ 1.05 kg/l (ISO 1183-1)
Skinning Time	~ 30 minutes (+23°C / 50% r.h.)
Curing Rate	~ 3 mm / 24h (+23°C / 50% r.h.)
Joint Dimensions	Min. width = 10 mm / max width = 35 mm
Sag Flow	0 mm, very good(20 mm profile, 23 °C) (ISO 7390)
Service Temperature	-40°C to +70°C

Mechanical / Physical Properties

Tensile Strength	~ 2,0 N/mm ² (ISO 37)
Tear Propagation Resistance	~ 4 N/mm ² (ISO34)
Shore A Hardness	~ 30 after 28 days (+23°C / 50% r.h.) (ISO 868)
Secant Tensile Modulus	0.30 N/mm ² approx. at 60 % elongation (23 °C) (ISO 8339)
Elongation at Break	~400% after 28 days (+23°C / 50% r.h.) (ISO37)
Elastic Recovery	70% after 28 days (+23°C / 50% r.h.) (ISO 7389)

System Information

Consumption / Joint Design	<p>The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥6 mm and ≤20 mm. A width to depth ratio of 2:1 must be maintained.</p> <p>Joints ≤10 mm in width are for crack control and therefore non-movement joints. What is relevant, is the joint width at the time of application of the sealant (guide value of +10 °C). For larger joints please contact our Technical Service Department.</p>
Substrate Quality	Clean and dry, homogeneous, free from oils and grease, dust and loose or friable particles. Cement laitance must be removed

Substrate Preparation / Priming

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Sikaflex® Crystal Clear adheres without primers and/or activators.

However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

Non-porous substrates

Aluminium, anodised aluminium, stainless steel, PVC, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of > 15 minutes (< 6 hours). Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of > 30 minutes (< 8 hours) before sealing the joints.

Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 8 hours).

For more detailed advice and instructions please contact the local Sika Technical Services Department.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

Substrate Temperature	+5°C min. / +40°C max.
Ambient Temperature	+5°C min. / +40°C max.
Substrate Moisture Content	Dry
Dew Point	Substrate temperature must be 3°C above dew point.

Application Instructions

Application Method / Tools

Sikaflex® Crystal Clear is supplied ready to use.

Bonding

After substrate preparation, apply Sikaflex® Crystal Clear in beads, strips or spots to the bonding surface in intervals of a few centimetres each. Use hand pressure only to set the element to be bonded into position. If necessary, use SikaTack® Panel Tape during the initial hours of curing. An incorrectly positioned element can easily be unfastened and repositioned during the first few minutes after application. Apply pressure again. Optimum bonding will be obtained after the complete curing of Sikaflex® Crystal Clear. The recommended adhesive layer thickness depends on surface evenness) is ≤3 mm. Fresh, uncured adhesive remaining on the surface must be removed immediately. Final strength will be obtained after complete curing of Sikaflex® Crystal Clear.

Sealing

After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sikaflex® Crystal Clear into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikaflex® Crystal Clear sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Do not use tooling products containing solvents.

Cleaning of Tools	Clean all tools and application equipment with Sika® Remover-208 / Sika® TopClean-T immediately after use. Hardened (cured) material can only be removed mechanically.
Notes on Application / Limitations	<ul style="list-style-type: none"> ▪ Before bonding, check adhesion and resistance of paints and coatings by carrying out a trail. ▪ Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation. However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product. ▪ Before using Sikaflex® Crystal Clear on natural stone, please refer to Sika Technical Services for advice. ▪ Do not use Sikaflex® Crystal Clear on bituminous sub- strates, natural rubber, EPDM rubber or on any build- ing materials which might bleed oils, plasticizers or solvents that could attack the sealant. ▪ Do not use Sikaflex® Crystal Clear to seal joints in and around swimming pools. ▪ Do not use Sikaflex® Crystal Clear for joints under wa- ter pressure or for permanent water immersion. <p>Do not use outside on easily corroding substrates such as blank steel or iron.</p>
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa

E-mail: headoffice@za.sika.com
Phone +27 31 792 6500
Telefax +27 31 700 1760
www.sika.co.za

