TECHNICAL DATA SHEET



11 February 2015, Rev 2



SOLIDKOTE IMPACT

HEAVY DUTY HIGH BUILD POLYURETHANE COATING

DESCRIPTION

SOLIDKOTE IMPACT is a protective, high build, polyurethane solventless, resin coating specifically developed to protect concrete and steel. Solidkote Impact exhibits excellent adhesion to various substrates including resistance to abrasion, chemical attack and other physical aggression, including minor movement. Supplied as a two-pack system comprising pigmented base and a hardener, it requires only on site mixing to produce an easily applied industrial floor finish. SOLIDKOTE IMPACT can be safely used in areas where contact with foodstuffs occurs or for coating potable water storage tanks.

ADVANTAGES

- Solvent free coating with full HACCP compliance.
- Easy to clean seamless finish.
- High order of durability and adhesion properties.
- Excellent flexibility
- Resistance to abrasion, impact, chemical attack and penetration.
- Low sensitivity to moisture.
- Easily application

APPLICATIONS

- Heavy duty industrial works spaces
- Chemical Processing
- Food preparation/wet areas
- Brewing/dairy clean areas
- Engineering and processing
- Tank linings
- Metal surfaces

Suitable substrates:

Concrete, polymer reinforced, grano concrete, asphalt, mild steel and wood.

TECHNICAL DETAILS

Appearance:	Semi-gloss, satin finish
Pot life at 20°c:	25 min
S.G:	1.5
Initial film set time at 20°c:	3 hours
Light traffic resistance:	12-16 hours
Heavy traffic resistance:	4 - 5 days
Coverage: Roller applied	30m ² / 5L kit @ 150um
Coverage: Trowel & spike roll	9m²/ 5L kit @ 500um
Bond to concrete:	>1.5 MPa
Application limits:	Temp: 0 - 30°c, RH. Max
	75%

PRECAUTIONS

Ensure substrate is fully dry not more than 10% moisture content. The storage, mixing and application conditions can affect the quality of the finish produced.

DIRECTIONS

- To be assured of maximum adhesion and physical/ chemical properties the correct surface preparation is essential. Removal of all pre-existing coatings via grinding methods is essential.
- Remove all grease, oils, debris and contaminants with a suitable degreasing cleaner. It is preferable to vacuum dry the substrate to speed up drying after cleaning. Ensure that the substrate is fully dry; where necessary a moisture test may be required.
- Prime the surface with Solidkote Impact primer. On metal substrates priming is not required. Ensure that the primer is uniform, where a matt finish is prevalent additional coats of primer should be applied until uniform visible seal. Apply the Solidkote Impact within 48 hours after the last primer coat has been applied.

Page 1 of 2

TECHNICAL DATA SHEET

SOLIDKOTE IMPACT

11 February 2015, Rev 2



We deliver results

- Mix the Solidkote Impact Resin to ensure a uniform mix. after which add the full contents of hardener and mix for 2 - 3 minutes until a uniform consistency is achieved.
- Pour the mixed product out onto the demarcated area. Using a steel trowel or notched rake spread at 300 - 500 µm. Spike roll to obtain a bubble and trowel mark free finish. Alternatively for coatings onto steel surfaces brush or roll out using a short Mohair roller.
- Maintain SOLIDKOTE IMPACT by regular scrubbing or mopping with Liquid Action (See TDS), will maintain this system in serviceable condition. Damaged areas of system should be patchrepaired/replaced in order to ensure longevity of the working area.
- The raw materials used in this system have been tested by Campden and Chorleywood (food authorities in Europe) as non-tainting and non-odour producing and suitable for use in food production areas.

Tel: +27 (0) 11 822 7242