



Versus Status Sheen (VSLs)

PRODUCT DESCRIPTION:

- A hardwearing high quality sheen finish flexible wall coating for interior and exterior use.

USES:

- Interior and exterior walls, ceilings, down pipes and gutters.
- Ideal for use on high traffic areas or surfaces that may require frequent washing.

FEATURES:

- Water based: Low odor and easy cleaning.
- Water resistance: Surpasses the SABS 0400:1900 Code of Practice rain penetration test over a 24 hour period.
- Excellent weather resistance.
- Quick Drying.
- Excellent exterior durability.
- Good color stability.
- Very good opacity, stain resistance and wash ability.

PRODUCT INFORMATION:

- Type: Modified Acrylic.
- Appearance: Sheen.
- Colors: White and a range of 16 Standard colors. Pastel, Medium and Deep tone colors can be tinted on request.
- Solids: 50 – 52% by mass.
- Density: 1.2 – 1.25 kg/l.
- Recommended Dry Film Thickness: 1 coat at minimum 35 µ and maximum 45 µ.
- VOC Levels: 20g/Lt.
- Viscosity at 25°C. : 95 -100 Krebs µ.
- Flash Point: Non-flammable.

APPLICATION DETAILS:

- Mixing: Stir well before use.
- Method: Sheepskin roller or brush. Can be applied using an airless spray gun.
- Thinning: Not recommended, but tap water if required. Thinning reduces the opacity.
- Clean up: Tap water.
- Spreading rate: 8 – 10 m²/l depending on surface porosity and profile.
- Viscosity 95-100 Krebs µ
- Relative Density 1.2 – 1.25
- Conditions: Avoid painting in wet or cold weather. Minimum temp 8°C
- Drying time: Touch dry ½ – 1 hour. Hard dry 4 hours at 25 degrees.
- Recoating time: 4 – 6 hours.

DISCLAIMER

The above information is given in good faith but without warranty due to the fact that the methods of application, location and condition of the substrates being coated are beyond our control.

- Requirements: 2 coats.

SURFACE PREPARATION:

- New Surfaces must be sound, clean and dry before painting.
- Concrete and cement should be filled with Versus Versafill.
- Gypsum Plaster should be primed with Versus Plaster Primer.
- Fiber Cement ceiling boards: the bare metal areas (nail heads) should be primed with Versus Steel Primer?
- Wooden surfaces should be primed with Versus Pink Wood primer.
- Galvanized Iron should be cleaned first with Versus Galvanized Iron Cleaner until a water break free surface has been achieved. Thereafter prime with Versus Galvanized Iron Primer and followed with Versus Universal Undercoat.
- Rusted Metals should be wire brushed or sanded to remove all rust. Prime with Versus Steel Primer. Thereafter apply Versus Universal Undercoat.
- PVC gutters and downpipes should be degreased and then abraded with fine sandpaper and then the topcoat can be applied directly.
- Previously Painted Surfaces must be sound, clean and dry before painting.
- After all surfaces are sound, clean and dry apply one coat of Versus Universal Undercoat as a tie coat. Other areas that have chalked and are powdery should be well sanded and sealed with Versus Plaster Primer.

STORAGE:

- Keep containers properly sealed.
- Store away from direct heat, sun and severe cold.

PACKAGING:

- 5 litres and 20 litres

PRECAUTIONS:

- Detailed safety information: refers to the material safety data sheet for this product.
- Do not apply directly to bare metal surfaces.
- Do not paint in wet or cold weather. (Minimum 8°C.)
- Drying times will be extended during wet or cold weather conditions.
- Do not apply direct to chalky or friable surfaces. Apply a penetrating coat of Versus Bonding Liquid or Versaprime Plaster Primer.