



SAINT-GOBAIN

duracure WPR

White Pigmented Resin

RESIN BASED CONCRETE CURING COMPOUND

DESCRIPTION

duracure WPR is a low viscosity, petroleum resin-emulsion curing compound for spraying onto the surface of concrete to give an effective and economical method of curing.

duracure WPR conforms to ASTM C309-19 Type 2 Class B.

USES

duracure WPR is very efficient for curing, where light reflectance is needed to keep the temperature of the concrete to a minimum.

ADVANTAGES

- duracure WPR** complies with the water retention and light reflectance requirements of ASTM C309-19 as a Type 2 Class B curing compound

TYPICAL PHYSICAL PROPERTIES

Specific gravity @ 25 °C	1.02 - 1.03
Solid content	32 - 34 %
Drying time	1 - 2 hours @ 23 °C

APPLICATION

duracure WPR is spray applied to the newly placed concrete, care being taken to ensure complete coverage of the surface. Various types of spraying equipment can be used i.e. Knapsack or motorized sprayers. Brush application can be used for smaller areas.

duracure WPR should be applied as soon as possible after the

concrete has been surface finished, i.e. trowelled, tamped or textured as required, but generally within 30 minutes or earlier if in conditions of hot sun or strong drying winds.

The nozzle of the sprayer should be held some 30 cm to 50 cm from the surface and passed slowly back and forth to ensure thorough coverage.

On vertical surfaces or soffits of concrete which may be partially dried out after being retained in shuttering for several days, it is imperative that the concrete should be well wetted before applying the curing compound. Never apply to dry or semi-dry concrete. To ensure the ultimate breakdown of the **duracure WPR** film, heavier coating should be avoided.

This coating will discolour the surface and therefore must not be used where aesthetics exposed surface finish requirements are a pre-requisite.

Curing membrane must be removed prior to overlayment with asphalt or other coatings/road-marking paint.

COVERAGE

The coverage of **duracure WPR** is dependent on the surface of the concrete as well as the means of application. For estimating purposes, a practical coverage between 4 - 7 m²/ℓ can be used.

PROTECTION ON COMPLETION

Protect surface against traffic and spillage until cured.

CLEANING

Immediately after use, spraying equipment should be cleaned out, especially the line and nozzle, with **abe® super brush cleaner**.

PACKAGING

200 ℓ; 25 ℓ.

HANDLING & STORAGE

duracure WPR is an emulsion and is non-flammable but should be stored away from combustible materials.

IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.®** endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot accept any liability for application – because **a.b.e.®** has no direct or continuous control over where and how **a.b.e.®** products are applied.

FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements.

a.b.e.® has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in building and construction technology.

Please consult our website for our latest data sheets.

DATE UPDATED: 21/06/2024

a.b.e.® is an ISO 9001:2015 registered company
Call: (+27) 860 223 773 | www.abe.co.za

