



SAINT-GOBAIN

flexothane® 45

**SINGLE COMPONENT HYBRID
CONSTRUCTION SEALANT /
ADHESIVE**

DESCRIPTION

flexothane® 45 is a thixotropic, VOC free moisture curing hybrid sealant/adhesive. It is a filled, moisture and oxidation resistant, mastic that exhibits excellent adhesion to cementitious and steel substrates.

USES

flexothane® 45 can be used as a general joint sealer on low movement joints, a crack filler on cementitious surfaces, and also as an adhesive on a wide range of substrates. It provides medium chemical, wear and corrosion resistance, while at the same time curing to a 45 Shore A hardness (± 45 Shore A). A degree of colour change with time is to be expected.

ADVANTAGES

- One-component, easy to gun
- Oxidation resistant
- VOC free
- Non-tack/does not pick up dirt
- Crack filler on cementitious substrates
- Good adhesion on the most common construction materials
- Good weathering and ageing properties
- Medium chemical and wear resistance

SURFACE PREPARATION

All surfaces are to be clean sound and free of moisture, dust, laitance and oil.

PRIMING

If applied to natural stone, we recommend the use of **flexoprime® 105**.

BACK-UP MATERIAL

Suitable back-up materials must be used to adjust sealant depth in the joint. **duracord®** is self-releasing material, but if **durasheet®**, soft-board or cork has been used as the joint filler and the sealant is going to be applied without **duracord®** a plastic strip bond breaker (polyethylene) must be placed on the filler surface before sealant is applied.

PROTECTION OF ADJACENT SURFACES

Masking tape applied to areas adjacent to the joint will protect them from contamination and enable the joints to be finished to a neat line. The masking tape should be applied after the joint has been prepared, prior to any priming or sealing operation and removed after all finishing and tooling operations have been completed, but before the sealant has cured.

TYPICAL PROPERTIES

Solids (%)	100%
Density	1.5 g/ml - Cured
Tensile Strength (MPa)	2.0 – 2.5
Elongation at Break (%)	$\pm 50\%$
Density	1.4 (Cured)
Shore A hardness	± 45
Viscosity mPas (S3, 10 rpm, 25C plate cone)	4 200 – 4 500
Cure Rate	± 1.5 to 2 mm per day (dependent upon relative humidity and temperature)
Application Temp	5 – 35 °C
Service Temp	50 °C Wet (continuous) 60 °C Dry (Intermittent)
Shelf Life	12 Months from date of manufacture
Storage Temperature	<25 °C (higher temperatures will reduce storage life)
Chemical Resistance	Dilute acids, dilute alkali and general chemicals
Pack Size	600 ml sausage
Colour	Grey, other colours against orders

APPLICATION

Place sausage in the barrel gun, cut end off of sausage and fit the nozzle; trim the tip to suit the joint spacing to be filled. Insert backing rod to the correct depth. Gun the product into clean joints that are free of loose material and laitance, then smooth with a dry spatula. The joint width should be designed to accommodate the expected movement, a width to depth ratio of 2:1 should be respected and a minimum width of 6 mm and a maximum of 20 mm should be adhered to (10 mm in depth).

TOOLING

Tooling of sealants is necessary to avoid air entrapment and to assist in wetting out the surfaces to which the sealant is applied. The surfaces of the joint should be smoothed with a clean knife or spatula. A mild solution of liquid soap and water can be sprayed onto the tooling spatula if required.

SPECIFICATION

The sealant will be **flexothane® 45**, a single-component, hybrid moisture curing sealant/adhesive that is VOC free applied in accordance with the recommendations of **a.b.e.®**

CLEANING

Tools should be cleaned immediately after use, and before the material has set, with **abe® super brush cleaner** followed by washing with soap and water.

PACKAGING

600 ml cartridges packed 12 per box.

HANDLING & STORAGE

This product has a shelf life of 12 months if kept in a dry cool place in the original packaging. In more extreme conditions this period might be shortened.

HEALTH & SAFETY

Uncured **flexothane® 45** is toxic and should not be allowed contact with skin and eyes. The use of gloves and eye protection is advised. Splashes into eyes should be washed immediately with plenty of clean water and medical advice sought. Ensure the working area is well ventilated during application and drying. Always wear gloves when working with the material and avoid excessive inhalation and skin contact.

Cured **flexothane® 45** is inert and harmless.

IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.®** endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot accept any liability for application – because **a.b.e.®** has no direct or continuous control over where and how **a.b.e.®** products are applied.

FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements.

a.b.e.® has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in building and construction technology.

Please consult our website for our latest datasheets.

DATE UPDATED: 30/10/2023

a.b.e.® is an ISO 9001:2015 registered company
Call: (+27) 860 223 773 | www.abe.co.za