

## JOINT SEALER 515 LM

Single Component Low Modulus Hybrid Sealant

Joint Sealer 515 LM is a thixotropic, solvent free, moisture curing, hybrid sealant. It exhibits low modulus and hardness combined with very high elongation properties. It has good moisture and oxidation resistance and excellent adhesion to most building substrates.

### APPLICATIONS

Joint Sealer 515 LM can be used both as a general joint sealer and crack filler on cementitious surfaces as well as where extremes of movement are anticipated where a low modulus, high elongation sealant is required. A degree of colour change with time is to be expected. It is not recommend for use in water retaining structures.

### DIRECTIONS

#### PREPARATION

All surfaces to be clean, sound and free of moisture and dust. Joints must be blown clean and dried with hot air if necessary. Remove dust, laitance and oil from all surfaces. If used in severe damp conditions, prime with SOLIDKOTE 110 wet-to-dry primer.

#### APPLICATION

Place sausage in the barrel gun, cut end off of sausage and fit the nozzle; trim the tip to suit the joint spacing to be filled. Insert backing rod to the correct depth. Gun the product into clean joints that are free of loose material and laitance, then smooth with a dry spatula. The joint width should be designed to accommodate the expected movement, a width to depth ratio of 2:1 should be respected and a minimum width of 6 mm should be adhered to and a maximum width of 20 mm (10 mm depth). A light damp cloth should be used to smooth off the surface of the Joint Sealer to give a uniform finish. Once cured, the surface of the

### TECHNICAL DETAILS

Appearance	Paste
Colours	Grey, White, Black, Beige, and custom on request
100% Modulus (MPa)	0.5 - 0.3
Tensile Strength (MPa)	1.10 – 1.30
Elongation at break (%)	>200
VOC	Complies
Solids Content	100%
Density (Cured)	1.4
Skin Cure	1 - 2 hours (dependent on thickness, % RH and temperature)
Cure Rate	2mm per day
Application Temperature	5 - 35°C
Service Temperature	60°C, dry
Storage	<25°C
Movement Capacity	25% of joint width
Chemical Resistance	Dilute acids, dilute alkalis and general chemicals
Pack Size	600 ml sausage
Cleaning	Solidkote 503 PU Thinner

product is paintable but check for elongation and compatibility before painting.

### CLEANING

Clean all tools and equipment immediately after use with SOLIDKOTE 503 PU Thinners, as the cured material is very difficult to remove. No other solvents are to be used.

#### Gauteng

35 Activia Rd, Activia Park, Germiston, 1610  
Tel: +27 11 822 7242

#### Kwa-Zulu Natal

41 Circuit Rd, New Germany, 3610  
Tel: +27 31 705 7733

#### Western Cape

Cnr Gunners Circle & Fisher Ave, Epping 1, 7475  
Tel: +27 21 535 4455

### HEALTH AND SAFETY:

Contact with the skin should be avoided by wearing gloves, eye protection and protective clothing. In case of eye contact wash well and obtain medical advice. The product contains a low level of free isocyanate.

Please read Safety Data Sheet and specific health and safety data for this product provided in compliance with the requirements of OHSA No.85 of 1993. The finished system is not hazardous to health or the environment.

### WARRANTY

Technical Finishes products are manufactured under high quality standards and are warranted against defective materials and are sold subject to standard Terms and Conditions of Sale, copies of which can be obtained upon request. Technical Finishes deals with approved applicators and carry a back to back warranty with these clients. Technical Finishes cannot be held responsible for the workmanship in surface preparation and application of our products, it is understood that the approved contractor will guarantee such workmanship and application. It is vital that the application is done in accordance to our specification.

---

#### **Gauteng**

35 Activia Rd, Activia Park, Germiston, 1610  
Tel: +27 11 822 7242

#### **Kwa-Zulu Natal**

41 Circuit Rd, New Germany, 3610  
Tel: +27 31 705 7733

#### **Western Cape**

Cnr Gunners Circle & Fisher Ave, Epping 1, 7475  
Tel: +27 21 535 4455