



Valdisole 704-706 6th Street, Wynberg, Sandton, 2090
info@versuspaint.co.za | T: (011) 885 3136 | F: (011) 885 1719
www.versuspaint.co.za | www.paintwithapurpose.co.za | www.specifications.co.za



Versus Masonry Surface Conditioner With Anti Fungal (VMP) Data sheet no 23-2015

PRODUCT DESCRIPTION:

Solvent based Acrylic Copolymer masonry surface conditioner.

USES:

- Used as a first coat on high Mpa masonry surfaces, gypsum plaster, friable concrete surfaces.

FEATURES:

- Can be over coated with most water and solvent based paints.
- Prevents water ingress but allows moisture to evaporate through the film.

PRODUCT INFORMATION:

- Type: Solvent based acrylic copolymer.
- Appearance: Matt.
- Colors: Off white only.
- Density: 1.30 - 1.35.
- Viscosity at 25°C (Stormer) : 60 – 65 K.U.s
- Flash Point: 36°C.

APPLICATION DETAILS:

- Mixing: Stir well before use.
- Method: Brush or roller. Can be sprayed.
- Thinning: Can be thinned up to 25% with Mineral Turpentine to assist penetration.
- Clean up: Mineral Turpentine.

- Spreading rate: 10 – 12 m²/l depending on surface porosity and profile.
- Conditions: Avoid painting in wet or cold weather. Minimum temp 8° C
- Drying time: Touch dry 1 hour. Hard dry 4 hours at 25 degrees.
- Recoating time: 4 hours.
- Requirements: 2 coats.

SURFACE PREPARATION:

- New Surfaces and previously painted surfaces must be sound, clean and dry before painting. Ensure substrates are free of any grease or oil by cleaning with Sugar Soap if necessary.

STORAGE:

- Keep containers properly sealed.
- Store away from direct heat, sun and severe cold.

PACKAGING:

- 20 Litres.

PRECAUTIONS:

- Detailed safety information: refers to the material safety data sheet for this product.
- Do not apply directly to bare metal surfaces.
- Drying times will be extended during wet or cold weather conditions.
- Thin and clean up only with Mineral Turpentine.

DISCLAIMER

The above information is given in good faith but without warranty due to the fact that the methods of application, location and condition of the substrates being coated are beyond our control.